



Liveo™ Pharma Advanced Pump Tubing

Silicone Tubing and Assemblies

Translucent pharmaceutical grade silicone tubing designed for pumping of ultrapure liquids in pharmaceutical and biotechnological manufacturing processes.

Made from biomedical grade tear resistant platinum-cured elastomer.

APPLICATIONS

For use in peristaltic pumps where durability is required. DuPont Advanced Pump Tubing offers up to four times the pump life of standard platinum cure silicone tubing

FEATURES & BENEFITS

- Up to four times the pump life of standard platinum cured silicone tubing
- Excellent flexibility
- Superior resiliency
- Low extractables
- Contains no organic plasticizers, phthalates or latex additives
- No peroxide by-products, chlorophenyls or PCBs
- Easily sterilized
- Non-wetting (hydrophobic) surface
- Made from BioMedical Grade elastomer that exceeds United States Pharmacopeia (USP®) Class VI Plastics Test requirements
- Meets European Pharmacopoeia monograph 3.1.9. "Silicone elastomer for closures and tubing"
- Manufactured to the principles of FDA 21 CFR 210/211 cGMPs for Pharmaceutical products
- Produced in a FDA registered (CFN 1816403) and inspected healthcare facility
- High purity quality (USP 788 Particulate matter for Injection, USP 85 Bacterial Endotoxins, ISO 11737-1 Bioburden)
- FDA 21 CFR 177.2600 and USP 661 Physico-chemical tests - Plastics
- Added pump life can reduce material usage and process shut downs
- Reduces risk of contaminating ultra-pure liquids
- Complete traceability
- Consistent performance
- Rigorous change control
- Outstanding filling accuracy

Common tubing product sizes (capability exists for these and many other sizes) and Burst properties:

Inside Diameter [mm]	Outside Diameter [mm]	Wall [mm]	Burst Pressure [bar]
3.2	6.4	1.6	5.4
4.8	8.0	1.6	3.8*
4.8	9.5	2.4	4.8



Liveo™ Pharma Advanced Pump Tubing

Silicone Tubing and Assemblies

6.4	9.5	1.6	2.8*
6.4	11.1	2.4	4.1*
6.4	12.7	3.2	5.2
8.0	12.7	2.4	3.4*
9.5	12.7	1.6	1.6*
9.5	14.3	2.4	2.9*
9.5	15.9	3.2	3.4
12.7	17.5	2.4	2.0*
12.7	19.1	3.2	2.6
15.9	22.2	3.2	2.3
19.1	25.4	3.2	1.7

Note: Burst pressure values are typical values not intended for writing specifications. Test method is based on ASTM D380-14.

* Predicted burst pressure : a regression formula was used to calculate burst pressure of these tubing sizes not actually tested for burst strength.

Quality information

The FDA registered and ISO 9001:2015 certified Healthcare Industries Materials Site (HIMS site) is responsible for ensuring consistent product quality.

Regulatory and Biocompatibility information

Product Regulatory Information document as well as Summary of health data are available from our DuPont website or upon request.

PACKAGING

To serve our customers better, we can provide Pharma Advanced Pump Tubing in a variety of dimensions, including the most commonly used sizes shown in Table above. Standard package is a 15-meter coil, double bagged in separately sealed polyethylene bags contained in a cardboard box.

Typical mechanical properties

Modulus at 200% strain	3 ^[1] MPa	ASTM D 412
Tensile Strength	8.9 MPa	ASTM D 412
Elongation at break	590 %	ASTM D 412
Shore A hardness	50	ASTM D 2240
Tear strength, die B	40.0 kN/m	ASTM D 624
[1]: die D		



Liveo™ Pharma Advanced Pump Tubing

Silicone Tubing and Assemblies

Storage and stability

Shelf life

1800^[2] days

[2]: * From the date of manufacture when stored in the original unopened containers

Characteristics

Food contact

FDA 21 CFR

Additional information

How to use

Information from “Chemical Resistance Guide For Elastomers IV”, published by Compass Publications, La Jolla, California, can be used as a reference. It is however recommended that the DuPont product be evaluated in the real conditions of use.

LIMITATIONS

This product is neither tested nor approved for any hospital or patient care use such as for temporary insertion or any in vivo procedures. This product is not to be used in human implantation, or human contraceptive, reproductive, obstetrical or gynecological applications. The user shall hold DuPont harmless from any and all damages resulting from use of this product. It is the sole responsibility of the user to determine the safety and efficacy of this product for any specific use. This product is not tested for specific pharmaceutical or medical device use(s). Should you wish to use this product in a specific pharmaceutical or medical device application, please contact DuPont to discuss such potential use. It remains the User's responsibility to ensure the safety, efficacy and legal and regulatory compliance in each relevant jurisdiction (including targeted geographic regions of manufacture and supply) of these materials for its intended uses. DuPont makes no representation concerning the suitability of these products for any particular medical or pharmaceutical application. Under no circumstances should these materials be considered for implantation into the human body for periods that exceed 30 days in duration.

Safety warning

Before handling, please consult the corresponding material safety data sheets. These are available upon request or can be downloaded from our DuPont website : www.DuPont.com



Liveo™ Pharma Advanced Pump Tubing

Silicone Tubing and Assemblies

Chemical Media Resistance

Sterilisation methods

- ✓ Ethylene Oxide
- ✓ Autoclave Steam, 30min at 120°C
- ✓ Gamma Radiation, 50 kGy

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

DuPont

Please refer to DuPont Medical Application Policy before any use of DuPont material in a medical application- [Position Statements | DuPont](#).

Do not use DuPont products in medical application involving permanent implantation (more than 29 days) in the human body or contact with internal body fluids or tissues (for more than 29 days) unless the product has been provided from DuPont under a written contract that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use.

Although these products may have been tested in accordance with certain USP Class VI or ISO 10993 standards, DuPont makes no representation or warranty, express or implied, regarding the suitability of its products for any particular healthcare or medical application, nor does it make any other representations or warranties based on such testing. Customers are solely responsible for determining whether DuPont products are suitable for their intended purpose and for ensuring legal and regulatory compliance of the product in final application. DuPont disclaims any and all liability for incidental, special, or consequential damages arising out of or relating to the customer's use of DuPont products.

The information, suggestions, and data (collectively referred to as "Information") set forth herein are based on technical data that DuPont believes to be reliable and fall within the normal range of properties. Such Information is provided for informational purposes only and is not intended to substitute for any testing necessary to determine the suitability of a particular material for a specific purpose. The Information is to be used and relied upon at the user's sole discretion and risk. DuPont makes no warranties, express or implied, and disclaims any and all liability, whether direct or indirect, for damages or losses arising out of or relating to the use of the Information, suggestions, data, or materials described herein.

Statements concerning the use of the products or formulations described herein are not to be construed as recommending the infringement of any patent, copyright, designs or other intellectual property and no liability for infringement arising out of such use is assumed by DuPont. None of this information is to be considered as a license to operate under, or recommendation to infringe, any patents.